#### **ACTEGA Terra GmbH**

Industriestraße 12, 31275 Lehrte, Germany
Tel +49 51 32 50 09-0, Fax +49 51 32 50 09-1 45
DownloadTDS.ACTEGA.Terra@altana.com, www.actega.com/terra



## **Technical Datasheet**

20.10.2017

## **TERRASCREEN UV Gloss Varnish G 22/680 NVK**

### **Product Description**

UV based screen varnish for uncoated paper with a very high viscosity.

The viscosity can be reduced by addition of max. 5 % TERRAADD UV Reactive Thinner G 13/141.

### **Properties during coating process**

Reactivity



### **Properties in the cured condition**

Gloss

Surface smoothness



# Performance during further processing

- · Hot foil stamping: no
- · Glueability: no

### **Material characteristics**

- · Delivery viscosity: high viscous
- Solids: > 98 %

### **Special properties**

- · very good flow out
- · The varnish contains optical brightener.
- · very good edge definition
- · low tendency to penetration

# Field of application

#### Application

- Screen printing
- Curing: 2 x 80 W/cm at max. 25 m/min. speed
- Recommended mesh: 77 . . . 55 L/cm
- The fine adjustement for the choice of tissue must be chosen individually depending job and motive.

### Substrates

- · coated paper
- uncoated paper

### Printing products

- · folding box, non food
- · commercial prints, covers
- · folding box, pharmaceuticals
- · folding box, cosmetics
- · displays

### Food legislation assessment

 For information about the food legislation classification about this product we ask you to contact our department for quality, environment and product safety.

T: +49 (0) 5132 5009-140

mail to: QUM.ACTEGA.Terra@altana.com

### **Processing recommendations**

- Stir up well before use!
   Mechanical stirring is recommended.
- The printing inks should be suitable for coating.
   The resistance against alkali, alcohol and solvents should be given in accordance to DIN ISO 2836, former DIN 16524, to exclude any colour change.
- · Glue flaps should be uncoated.
- A strong absorption on absorbent surfaces can cause an insufficient curing of the UV varnish, sensory problems, mechanical influence as well as rub resistance problems and poor slip properties.
- The total structure of substrate/printing ink/varnish must be cured sufficiently before processing and should be checked during the process.
- The property profile of the coating film is given in case of a complete curing.
   The curing depends on the efficiency of lamps, life of UV lamps, machinery speed, general conditions of the UV unit (reflectors, etc.), temperature and the distance from the UV unit to the substrate.
   We recommend to clean regularly the reflectors and if necessary to change the lamps in case of a drop in lamp efficiency.

### Cleaning

 Please clean machine and tools immediately with the right screen cleaner or alcohol.



## **Technical Datasheet**

20.10.2017

## **TERRASCREEN UV Gloss Varnish G 22/680 NVK**

#### Storage

- · Shelf-life from date of dispatch 6 months
- Applies to closed original containers at 5°C up to 30°C.
- The increase of viscosity is possible if the coating is stored wrong or for a longer time!
- · Place under the exclusion of light.
- · Keep from freezing, heat and solar radiation.
- Do not pollute the varnish with washing water, cleaning agent or other varnishes/adhesives.

#### **Safety instructions**

- If the varnish comes into contact with eyes please remove contact lenses and keep the eyelids open.
   Clean with plenty of water (10 - 15 min).
- Clean and rinse immediately with water and soap if the varnish comes into contact with the skin.
   Do not use solvents or dilutions.
   Contaminated clothing should be removed immediately.
- Please pay attention to the information given in the material safety data sheet.

# **Environmental recommendation**

- Please pay attention to the information given in the material safety data sheet.
- Do not give the varnish into lakes and rivers or the sewage system.
- Remainders must be disposed professionally in compliance with valid instructions.

#### Please be advised

- All information provided on this product (in this sheet or elsewhere) are made to the best of our knowledge.
- This data sheet does not claim to be complete.
- All information are technical quality descriptions, advisory and due to the wide range of materials, production conditions, operations and processes do not release from own tests and examinations in customer-specific circumstances.
- If an application is intended to be made under different conditions than those specified in this sheet, we only assume liability after having examined the respective different conditions.

 We reserve the right to change product characteristics because of technical progress, amendment of applicable law and mandatory production-related needs.